

FluorTech

Product Data sheet

PTFE (high-modulus) tape type HM-350 Self-Adhesives thickness 0.051mm

Typical properties	unit	value	test method
Thickness	mm	0.064mm	FTMS 191A-5030
Total Thickness	mm	0,089mm	
Adhesion to steel	g/cm	276	
Tensile strength	N/cm	45	FTMS 191A-5102
Elongation	%	150	
Dielectric Strength	kV	8	ASTM D149-81
Temperature Resistance	°C	-73/+260	N/A
Insulation class	°C	180	
Adhesive type	S	Silicone	

The data listed herein fall within the normal range of product properties for the products described, but they should not be used to establish specification limits nor used alone as the basis of design. We assumes no obligation or liability for any advice furnished by it or for results obtained with respect to these products. All such is provided gratis and buyer assumes sole responsibility for results obtained in reliance thereon. We warrants that the material itself does not knowingly infringe any patent, but no license is implied nor is any further warranty made.

FluorTech BV

Newtonstraat 20

1704 SB Heerhugowaard, Netherlands

Phone no. +31 (0) 72-5745644

telefax +31 (0) 72-5717417

Email: info@fluortech.nl

Website: www.fluortech.nl