

# FluorTech

## Product Data sheet

Skived PTFE film style SPSA-3S with Silicone Adhesive thickness 0.08mm

Typical properties	unit	value	test method
Weight without Adhesive	g/m <sup>2</sup>	172	FTMS 191A-5041
Thickness	mm	0,08	FTMS 191A-5030
Total Thickness	mm	0,124	
Tensile strength	N/cm	39	FTMS 191A-5102
Minimum Elongation	%	200	
Temperature Resistance	°C	-40/+260	N/A
Peel adhesion	N/cm	5,4	ASTM D3330-83
Adhesive type	S	Silicone	
Standard width	mm	990	

The data listed herein fall within the normal range of product properties for the products described, but they should not be used to establish specification limits nor used alone as the basis of design. We assume no obligation or liability for any advice furnished by it or for results obtained with respect to these products. All such is provided gratis and buyer assumes sole responsibility for results obtained in reliance thereon. We warrant that the material itself does not knowingly infringe any patent, but no license is implied nor is any further warranty made.

### **FluorTech BV**

Newtonstraat 20

1704 SB Heerhugowaard, Netherlands

Phone no. +31 (0) 72-5745644

telefax +31 (0) 72-5717417

Email: [info@fluortech.nl](mailto:info@fluortech.nl)

Website: [www.fluortech.nl](http://www.fluortech.nl)