

FluorTech

Product Data sheet

UHMWPE -film Self-Adhesive thickness 0.13mm

Typical properties	unit	value	test method
Weight without adhesive	g/m ²	120 ± 5%	ASTM D751-00
Thickness without adhesive	mm	0.127mm	ASTM D751-00
Total Thickness	mm	0,18mm	
Adhesion	g/cm	725	ASTM D751-00
Breaking strength	kg/cm	12,5	
Maximum Temperature	°C	-40/+90	
Max. Width	mm	610mm	
Elongation	%	225	
Adhesive type	A	Acrylic	

The data listed herein fall within the normal range of product properties for the products described, but they should not be used to establish specification limits nor used alone as the basis of design. We assumes no obligation or liability for any advice furnished by it or for results obtained with respect to these products. All such is provided gratis and buyer assumes sole responsibility for results obtained in reliance thereon. We warrants that the material itself does not knowingly infringe any patent, but no license is implied nor is any further warranty made.

FluorTech BV

Newtonstraat 20
1704 SB Heerhugowaard, Netherlands
Phone no. +31 (0) 72-5745644
telefax +31 (0) 72-5717417
Email: info@fluortech.nl
Website: www.fluortech.nl